Low-Frequency Noise in High-k LaLuO₃/TiN MOSFETs

Maryam Olyaei, B. Gunnar Malm, Per-Erik Hellström, and Mikael Östling

KTH – Royal Institute of Technology, Integrated Devices and Circuits,
School of Information and Communication Technology P.O. Box 229, SE-16440 Kista, Sweden, olyaei@kth.se

Abstract— Low-frequency noise (LFN) characterization of high-k LaLuO₃/TiN nMOS transistors is presented. The experimental results including the noise spectrum and normalized power noise density and mobility are reported. The noise results were successfully modeled to the correlated number and mobility fluctuation noise equation. High-k dielectric devices show lower mobility and roughly one to two orders of magnitude higher low-frequency noise which is comparable to the hafnium based oxide layers. The implementation of higher-k LaLuO₃ seems to be a suitable candidate to the tradeoff between equivalent oxide thickness scaling and low frequency noise.

Keywords: Low-frequency noise, high-k dielectrics, mobility degradation, charge traps, characterization.

1. INTRODUCTION

Advanced gate stacks are promising materials in order to enable the progress of MOSFET scaling [1]. Applying a high-k dielectric reduces the equivalent oxide thickness (EOT) while keeping the leakage current low. Hafnium based dielectrics with $k \sim 22$ have been used as high-k dielectrics successfully in the CMOS technology [2]. However, in order to keep the scaling trend ongoing the implementation of higher-k dielectrics with a suitable metal gate is inevitable. A good alternative is Lanthanum Lutetium oxide (LaLuO₃) with $k \sim 30$ which promises EOT values lower than 1nm with a low leakage current [3]. This high-k material is reported to have excellent thermodynamic stability up to $\sim 1000^\circ\text{C}$ which can be an advantage in the gate-first process. Furthermore it has an optical band gap around 5.2 eV with a symmetrical 2.1eV conduction and valence band offset to Si. Previous studies on LaLuO₃ includes the integration of LaLuO₃ on SOI MOSFETs [4], mobility studies on these transistors [5] investigating the trapping/detrapping of charges on LaLuO₃ MOS capacitor [6], deposition on Germanium-on-insulator substrates [7] and deposition on AlGaN/GaN MISHEMTs [8]. Although advantageous, there are still main issues that need to be considered in high-k devices. The high-k dielectric introduces more interface and bulk traps leading to instability in threshold voltage, mobility degradation and $1/f$ noise level increment. The reported number of negative trap states per unit area for a LaLuO₃ MOS capacitor is $N_t = 2.2 \times 10^{11} \text{ cm}^{-2}$ and for positive charges $N_t = 6.6 \times 10^{11} \text{ cm}^{-2}$ [6].

The main focus of this work is on low-frequency noise since excessive level of LFN noise can be a major concern in stability and reliability of electronic circuits. According to table RFAMS1 of the ITRS roadmap [1], the $1/f$ noise needs to meet more strict requirements for RF and analogue mixed signal CMOS technology. This topic is even more challenging in the new technology devices as this noise increases with device scaling.

The low-frequency noise in MOSFETs which is investigated through the drain current can be due to carrier number fluctuations, mobility fluctuations or a result of both. Based on comprehensive studies in this area, it is considered that $1/f$ noise can be analyzed in MOSFETs and modeled considering the mechanisms originating the noise.

In this work, for the first time, the low-frequency noise in high-k LaLuO₃/TiN metal gate n-type transistors is measured and discussed. Additional studies on the mobility helped determine the physical explanation behind the source of noise in these devices better.

This article is organized as followed: In section 2 the device fabrication and experimental details are explained. The results of low-frequency noise and mobility measurements are reported in section 3 followed by fitting a noise model to the results for these devices. Finally, the conclusions are summarized in section 4.

2. FABRICATION AND EXPERIMENTAL DETAILS

2.1 Device Fabrication

These devices were fabricated on a 30 nm thick SIMOX SOI substrates. The thickness of silicon was reduced through sacrificial dry oxidation and HF wet etching. This was followed by MESA etching to define active areas. The composition of gate stacks is different among the wafers and is summarized in Table I. The reference wafer has no high-k dielectric layer. In other wafers, the high-k dielectric with different thicknesses (t_{hk} = 6 nm, 20 nm) was deposited by MBE. In one of the wafers a 5 nm interfacial oxide layer was placed beneath the high-k layer. In the next step, TiN metal gate was deposited by sputtering on all wafers followed by deposition of in-situ phosphorus doped poly-Si (t_{poly} =150 nm). After the gate dimensions were defined through I-line lithography, poly-Si/TiN etch was performed. PtSi Schottky-barrier source/drain was formed and implanted with arsenic for nMOSFETs. To enable dopant segregation at the PtSi/Si interface, RTA at 700°C was carried out. LTO oxide deposition, contact hole patterning, metallization and FGA (10% H₂ in N₂ at 400° C for 30 min) finalized the fabrication process.

TABLE I. COMBINATION OF THE GATE STACKS

<i>Wafer</i>	<i>SiO₂ thickness (nm)</i>	<i>LaLuO₃ thickness (nm)</i>	<i>TiN thickness (nm)</i>
Reference	5	NA	20
High-k 1	5	6	20
High-k 2	NA	6	20
High-k 3	NA	20	20

2.2 Experimental

The low-frequency noise measurements were carried out on nMOS devices on four different wafers described above. Different gate lengths (L_G = 0.35, 0.5, 1 μ m) and gate widths (W_G = 10, 50 μ m) were investigated. The gate voltage was stepped from subthreshold to strong inversion region at two different drain biases V_{DS} =50 mV (linear region) and V_{DS} = 1V (saturation region). The measured frequency range was chosen to be between 1 and 100 Hz. The low-frequency noise measurement setup consists of a Programmable Biasing Amplifier (PBA) with an external low noise power supply and a spectrum analyzer.

For the mobility measurements, the drain conductance method is used and N_{inv} is obtained from gate to channel conductance. The mobility parameter was extracted for the four different wafers. The largest area devices (W =50 μ m, L =3 μ m) were chosen for this measurement.

3. RESULTS AND DISCUSSION

3.1 Mobility

The channel mobility in MOSFETs is a critical parameter which has been vastly studied and successfully modeled for standard MOSFETs. However, there are additional factors limiting the mobility in high-k MOSFETs leading to a lower mobility in these devices. The mobility degradation is mainly originated from scattering due to charges in the high-k and at the interface, surface roughness scattering, remote Coulomb scattering and remote phonon scattering [9] [10] [11]. The latter appears only in high-k transistors.

The mobility parameters extracted by applying the approximated Q_{inv} method versus the inversion charge density are plotted in Fig. 1. The mobility degrades from the reference wafer to high-k3 due to increased number of traps as expected. Roughness scattering seems to be the dominant scattering mechanism in the reference and high-k 1 wafer. A large variation in mobility is observed in the high-k1 devices which is related to poor interface between oxides. This is also seen in the threshold voltage shift among different dies of this wafer. The reference wafer shows stable mobility behavior and threshold voltage. No statistics could be achieved for high-k2 and high-k3 wafer due to high gate leakage current.

Fig. 1 Mobility versus inversion charge density measured on $W=50\text{ }\mu\text{m}$, $L=3\text{ }\mu\text{m}$ n-type devices.

Fig. 2. N-type device $W=10\mu\text{m}$, $L=0.5\mu\text{m}$ noise spectrum extracted from the reference wafer.

3.2 Low-frequency noise

The drain current noise spectrum between 1-100Hz for an n-type LaLuO₃/TiN MOSFET is shown in Fig. 2. The gate voltage ranges from $V_{GS} = 0\text{ V}$ to 1.6 V . The threshold voltage (V_T) of this device was around 0.5 V which was extracted through measurements of the slope at maximum g_m of I_D - V_{GS} curve. The noise level follows the gate bias clearly. A similar $1/f$ behavior is shown in all the devices ($0.8 < \gamma < 1.2$). However these devices seem to show an obvious $1/f$ behavior at gate biases higher than the threshold voltage while a less steep slope is observed at lower gate voltage biases which shows the background noise.

To verify the reproducibility of the data, a device to device comparison is investigated. This comparison for n-type devices is shown in Fig. 3 and Fig. 4, for the reference wafer and high-k 1 wafer respectively. These plots show the normalized drain current noise (S_{ID}/I_D^2) measured at $f=10\text{ Hz}$ versus the drain current. The measurements were performed at two different drain bias voltages which is observable in the plots. As depicted, the two plots overlap well especially in the strong inversion region. In Fig. 5, the devices are compared in a geometrical point of view. The $1/f$ noise is expected to increase as the inverse of device area. The smallest device ($W=10\text{ }\mu\text{m}$, $L=0.35\text{ }\mu\text{m}$) shows the highest noise level while the longest device ($W=10\text{ }\mu\text{m}$, $L=1\text{ }\mu\text{m}$) shows the lowest noise level. The widest device ($W=50\text{ }\mu\text{m}$, $L=0.35\text{ }\mu\text{m}$) device has a low level of noise and also higher drain current.

Fig 3. Device to device comparison for a $W=10\text{ }\mu\text{m}$, $L=0.35\text{ }\mu\text{m}$ nMOS at $f=10\text{ Hz}$ on the reference wafer.

Fig 4. Device to device comparison for a $W=10\text{ }\mu\text{m}$, $L=0.35\text{ }\mu\text{m}$ nMOS at $f=10\text{ Hz}$ on the high-k 1 wafer

Fig 5. Comparison between three different geometries on the same die for the nMOS devices at $f=10$ Hz and $V_{DS}=50$ mV on the reference wafer.

Fig 6. Normalized drain current noise versus drain current for n-type devices with $L=0.5$ μm and $W=10$ μm at $f=10$ Hz and $V_{DS}=50$ mV on the reference, high-k 1 and high-k 2 wafer.

In Fig. 6, S_{ID}/I_D^2 at $f=10$ Hz over the drain current is depicted for different devices on the reference, high-k 1 and high-k 2 nMOS wafers. In order to fit an appropriate noise model, these noise plots were compared to $1/I_D^2$ and $(g_m/I_D)^2$. All n-type devices show a $1/I_D^2$ dependence. Also a good correlation is shown between the normalized drain current noise and $(g_m/I_D)^2$ for high drain currents especially in nMOSFETs which is shown in Fig. 7, 8 and 9.

These results suggest a correlated number fluctuation and mobility noise model. The normalized drain current noise for a correlated noise model can be expressed as [12]:

$$\frac{S_{ID}}{I_D^2} = \frac{q^2 k T \lambda N_t}{W L C_{ox} f^\gamma} \frac{g_m^2}{I_D^2} \left(1 + \frac{\alpha \mu_{eff} C_{ox} I_D}{g_m}\right)^2 \quad (1)$$

Where g_m is the transconductance, μ_{eff} the mobility, λ the tunneling attenuation distance, N_t the volumetric oxide trap density (eV/cm^3), α the scattering parameter V_s/C , L the gate length, W the gate width, C_{ox} the gate oxide capacitance, k the Boltzmann's constant, T the absolute temperature and γ the characteristic exponent.

Fig. 7. Normalized drain current noise over drain current compared to $(g_m/I_D)^2$ for an n-type device on the reference wafer with $W=10$ μm , $L=0.5$ μm at $f=10$ Hz.

Fig. 8. Normalized drain current noise over drain current compared to $(g_m/I_D)^2$ for a high-k2 n-type device with $W=10$ μm , $L=0.5$ μm at $f=10$ Hz.

Fig. 9. Normalized drain current noise over drain current compared to $(g_m/I_D)^2$ for a high-k3 n-type device with $W=10\ \mu\text{m}$, $L=0.5\ \mu\text{m}$ at $f=10\text{Hz}$.

Fig. 10. Normalized input gate voltage noise measured at $f=10\text{Hz}$ and $V_{DS}=1\ \text{V}$ versus I_D/g_m and extrapolated data using (1) for n-type $W=10\ \mu\text{m}$, $L=0.5\ \mu\text{m}$ devices on all four samples.

In this noise model, the interaction between traps in the gate oxide and channel carriers is the main source of noise which contributes to the first part of the equation. On the other side, this trapping and releasing of carriers affects the mobility, which is taken into account in the second part of the equation modeled with α . This parameter defines the strength of the correlated mobility. The reported values are usually around $1 \times 10^4\ \text{Vs/C}$ for nMOSFETs [13].

α and N_t for all four samples are extracted through extrapolation from experimental data using (1). The parameter α , is constant $1 \times 10^4\ \text{Vs/C}$ as expected for nMOSFETs. N_t varies for one decade from the reference wafer to high-k. The simulated values are summarized in Table II which are comparable to N_t in HfO_2 MOSFETs [14].

TABLE II. N_t AND ALPHA VALUES FOR ALL SAMPLES

Wafer	$N_t\ (\text{cm}^{-3}\text{eV}^{-1})$	$\alpha\ (\text{Vs/C})$
Reference	1×10^{17}	1×10^4
High-k 1	2×10^{17}	1×10^4
High-k 2	2×10^{18}	1×10^4
High-k 3	2×10^{18}	1×10^4

The input gate voltage noise ($S_{VG}=S_{ID}/g_m^2$) which is normalized is plotted over I_D/g_m for n-type $W=10\ \mu\text{m}$, $L=0.5\ \mu\text{m}$ devices of four samples under study in Fig 10. As expected, advanced gate stacks show a higher level of noise comparing to the reference wafer however this is comparable to the noise level in hafnium based oxide gates. Applying the interfacial oxide layer reduces the noise level significantly. Considering the variations, the enhancement in the noise level of high-k devices can differ between one and two orders of magnitude. According to this figure, same level of noise is obtained for high-k 2 and high-k 3 devices. This confirms that only the traps close to the channel take part in the fluctuations therefore thicker deposited layer of high-k will not influence the low-frequency noise.

4. CONCLUSION

Low frequency noise on $\text{LaLuO}_3/\text{TiN}$ nMOS transistors has been characterized for the first time. The noise behavior in nMOSFETs is shown to be compatible with the correlated number and mobility fluctuations model. The results indicate that the noise level in high-k devices is one to two orders of magnitude higher than the standard MOSFETs. However the implementation of an

interfacial oxide layer reduces the noise level significantly. It can be concluded that in the challenging trade-off between aggressive equivalent oxide thickness scaling and an acceptable low-frequency noise level, LaLuO₃ can be considered as a qualified alternative.

ACKNOWLEDGEMENTS

The authors would like to thank Joao Marcelo Lopez, Siegfried Mantl and J. Schubert at Forschungszentrum Juelich and H. Gottlob and M. Schmidt at AMO for the fabrication of the high-k metal gate stacks. This work was financially supported by the Swedish Science Council through the “Fundamental noise studies on strain-engineered and high-mobility nano-scale transistors “ project and European Research Council (ERC) Advanced Investigator Grant to M. Östling.

REFERENCES

- [1] 2008 Update International Technology Roadmap for Semiconductors.
- [2] J. H. Choi, "Development of Hafnium based high-k materials_A review," Elsevier SD Freedom Collection, vol. 72, nr 6, pp. 97-136, 2011.
- [3] H. Wang, "Atomic Layer Deposition of Lanthanum-Based Ternary Oxides," *Electrochemical and Solid-State Letters*, Jan. 2009.
- [4] E. D. Özben, "Integration of LaLuO₃ (k~30) as High-k Dielectric on Strained and Unstrained SOI MOSFETs with a Replacement Gate Process," *IEEE Electron Device Letters*, vol. 32, nr 1, pp. 15-17, Jan 2011.
- [5] W. Yu, "MOSFETs with High Mobility Channel Materials and Higherk/Metal Gate Stack," *Solid-State and Integrated Circuit Technology (ICSICT)*, 2010.
- [6] N. Sedghi, "CV measurements on LaLuO₃ stack metal-oxide-semiconductor capacitor using a new three pulse technique," *American Vacuum society*, Jan. 2011.
- [7] J. J. Gu, "high Performance Atomic-Layer-Deposited LaLuO₃/Ge-on-Insulator p-Channel Metal-Oxide-Semiconductor Field-Effect-Transistor with Thermally Grown GeO₂ as Interfacial Passivation Layer," *Applied Physics Letter*, July 2010.
- [8] S. Yang, "Characterization of High LaLuO₃ Thin Film Grown on AlGaIn/GaN Heterostructure by Molecular Beam Deposition," *Applied Physics Letter*, 2011.
- [9] M. v. Haartman, "Comprehensive Study on Low-Frequency Noise and Mobility in Si and SiGe pMOSFETs with High-k Gate Dielectrics and TiN Gate," *IEEE Transactions on Electron Devices*, 2006.
- [10] Z. Ren, "Inversion Channel Mobility in High-k High Performance MOSFETs," *IEEE*, 2003.
- [11] D. Casterman, "Evaluation of the Coulomb-Limited Mobility in High-Dielectric Metal Oxide Semiconductor Field Effect Transistors," *Journal of Applied Physics*, 2010.
- [12] G. Ghibaudo, "Electrical Noise and RTS Fluctuations in Advanced CMOS Devices," *Microelectronics Reliability*, vol. 42, pp. 573-582, 2002.
- [13] M. v. Haartman, *Low-Frequency Noise in Advanced MOS Devices*, Springer, 2007.
- [14] O. Ghobar, D. Bauza och B. Guillaumot, "Defects in the Interfacial Layer of SiO₂-HfO₂ gate stacks: Depth Distribution and identification," *IEEE*, 2007.